

Mixing ratio A(white) : B(blue)	1 : 1
Mixing under vacuum	40 sec
Working time at 23 °C	> 5 min
Curing time at 23 °C	30 - 45 min
Tear resistance (DIN 53504)	ca. 1,8 N/mm ²
Elongation at tear (DIN 53504)	ca. 220 %
Tear growth resistance (ASTMD 624 B)	ca. 3,0 N/mm ²
Shore A hardness at 60 min.	> 16 - 18