

Mixing ratio A(white) : B(blue)	1 : 1
Mixing under vacuum	40 sec
Working time at 23 °C	ca. 4 min
Curing time at 23 °C	ca. 30 min
Tear resistance (DIN 53504)	ca. 2,5 N/mm ²
Elongation at tear (DIN 53504)	ca. 200 %
Tear growth resistance (ASTMD 624 B)	ca. 7,0 N/mm ²
Shore A hardness at 60 min.	18 - 20
Color	-